



**Regiment 150 HEM  
#39235**

Typical Physical Properties

<b>Property</b>	<b>Unit of Measure</b>	<b>Typical Value</b>	<b>Test Method</b>
<b>Weight</b>	osy	1.4	ASTM D3776
<b>Elongation @ Peak</b>	%		ASTM D5034-09
<b>MD</b>		45.6	
<b>CD</b>		55.5	
<b>Tensile @ Break</b>	lbs		ASTM D5034-09
<b>MD</b>		31.0	
<b>CD</b>		23.1	
<b>Trap Tear</b>	lbs		ASTM D 5733-99
<b>MD</b>		6.2	
<b>CD</b>		8.8	
<b>Air Permeability</b>	CFM	224.3	ASTM D737

Reviewed  
11-19-2013

The information presented herein, while not guaranteed, is to the best of our knowledge true and accurate. Except when agreed to in writing for specific conditions of use, no warranty or guarantee expressed or implied is made regarding the performance of any product, since the manner of use and handling are beyond our control. Nothing contained herein is to be construed as permission or as a recommendation to infringe any patent. This information reflects typical properties and should not be considered as specifications.